

- Bensew -

	Type	L #	Hits	Search Text	DBs	Time Stamp
1	BRS	L1	5	coating same substrate same capacitance same thickness same measure	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	2005/02/25 11:03
2	BRS	L2	473	324/662.ccls.	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	2005/02/25 11:52
3	BRS	L3	167	l2 and thickness	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	2005/02/25 11:04
4	BRS	L4	324	324/671.ccls.	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	2005/02/25 12:07
5	BRS	L5	196	l4 and thickness	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	2005/02/25 12:07
6	BRS	L6	0	l4 same thickness	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	2005/02/25 12:07
7	BRS	L7	0	324/671.ccls. same thickness	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	2005/02/25 12:08
8	BRS	L8	196	324/671.ccls. and thickness	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	2005/02/25 12:08
9	BRS	L9	39	l8 and coating	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	2005/02/25 12:08
10	BRS	L10	10	324/635.ccls. and thickness and coating	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	2005/02/25 12:37

	Type	L #	Hits	Search Text	DBs	Time Stamp
11	BRS	L11	17	"3801900"	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	2005/02/25 12:51
12	BRS	L12	4	"5382911"	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	2005/02/25 12:51

Benson

	Type	L #	Hits	Search Text	DBs	Time Stamp
1	BRS	L1	1015	"5942733" "6066574" "4472758" "4781968" "4805070" "4831493" "4865875" "5262754" "5357399" "5380341" "5424244" "5479716" "5512836" "5541564" "5559665" "5682059" "5768088" "5776660" "5849043" "5960315" "6096174" "6194650" "6214748" "6214748" "3648218" "4252838" "4261086" "4285117" "4296144" "4307373" "4316279" "4328646" "4333808" "4337115" "4369242" "4386453" "4424419" "4434084" "4453199" "4455039" "4462062" "4490945" "4538252" "4542580" "4571543" "4584761" "4789885" "4794439" "4823205" "4853341"	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	2005/02/25 17:31
2	BRS	L2	468	l1 and capacitance	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	2005/02/25 17:31
3	BRS	L3	366	l2 and thickness	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	2005/02/25 17:31
4	BRS	L4	169	l3 and coating	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	2005/02/25 17:31
5	BRS	L5	156	l4 and substrate	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	2005/02/25 17:32